

**PRACTICAL SOUND ABSORPTION COEFFICIENT α_p
OF SUSPENDED CEILING PANELS**

Test 5
Date 12/12/17
Station ALPHA

AA45

REQUESTER, MANUFACTURER SAINT-GOBAIN ECOPHON
NAMES Focus Ds with Extra Bass
CONFIGURATION 200 mm overall depth of construction
STANDARDS EN ISO 354, EN ISO 11654, EN 16487
FITNESS FOR PURPOSE Unchecked


MAIN CHARACTERISTICS

Dimensions in mm : 3000 x 3600
Area in m² : 10.80
Thickness in mm : 70
Mass per unit area in kg/m²: 3.22
Mounting type : E-200

MEASUREMENT CONDITIONS

Empty room: Temperature: 21 °C
Relative humidity: 50 %
Room with sample: Temperature: 21 °C
Relative humidity: 52 %

RESULTS



f	α_s	α_p
100	0,59	
125	0,75	0,75
160	0,94	
200	0,82	
250	0,85	0,80
315	0,79	
400	0,78	
500	0,80	0,80
630	0,85	
800	0,81	
1000	0,85	0,85
1250	0,94	
1600	0,97	
2000	1,00	1,00
2500	1,00	
3150	1,06	
4000	1,05	1,00
5000	1,10	
Hz		

$\alpha_w = 0,85$ (H)*
classement / class B

NRC = 0,85
SAA = 0,87

* It is strongly recommended to use this single number rating in combination with the complete sound absorption coefficient curve.